



SC8 GLAZE PUTTY

Universal Finishing Putty

A) DESCRIPTION AND FIELDS OF APPLICATION:

Finishing polyester putty used in car refinishing to cover coarse body fillers. It is used also to cover and fill imperfections and superficial pores. SC8 has a fluid aspect and after mixing with peroxide hardener it increase in viscosity/thixotropy. Ultra fast curing in low thickness.
VOC less of 250 g/L (2.09 lbs/US gal) according 2004/42CE.

B) TECHNICAL DATA:

Composition	Unsaturated polyester resins and special fillers
Specific weight	1.20 ± 0.05 kg/L (10.01 ± 0.42 lbs/US gal)
Available colours	Yellow
Safety data	See safety data sheet

C) SURFACE PREPARATION :



* Steel, Aluminium, Steel galvanised : Sand with P120 and degrease with V09

* Body Filler : Sand with P120-P220 and degrease with V09



* Clean well the surface to be treated with V09 Antisil. Make sure it is dry and free from silicone, wax, grease and any extraneous material.

* On base coats or enamel top coats, sand and clean the surface before applying the filler.

D) CAUTIONS:

* Mix the filler carefully with 1-3% paste hardener. Do not exceed with the hardener to avoid risk of staining during the painting operations.

* Do not use when temperature is below 5°C (41°F).

* Store in a cool and dry place.



E) PROCESSING:



1-3% paste hardener
pot life 3-5 min a 20°C (68°F)



application with putty knife



< 25 min at 20°C (68°F)



4-5 min at 1 mt (3.28 ft)



P220- P240 -P320 finishing

F) TOOLS CLEANING:

* With nitro or washing thinner.

G) RECOATING :

Primer F01 UV
Polyester Spray F18
Primers PUR F30, F31, F32, F33, F35 3 F36
Acrylic Primers F56, F57, F58, F59, F77, F78, F76, F79

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained